


Original

<p>1. Products consigned from (Exporter's business name, address, country)</p> <p>GUANGXI FORDE IMP. &amp; EXP. CO., LTD NO. 2, BUILDING 3, BAIYUN ANZHI DISTRICT, NO. 1 OF TIANXIN ROAD, PINGXIANG TOWN, PINGXIANG CITY, GUANGXI, CHINA</p>		<p>Reference No. E235794473100775</p> <p><b>ASEAN-CHINA FREE TRADE AREA PREFERENTIAL TARIFF CERTIFICATE OF ORIGIN (Combined Declaration and Certificate)</b></p> <p><b>FORM E</b></p> <p>Issued in <u>THE PEOPLE'S REPUBLIC OF CHINA</u> (Country)</p> <p>See Overleaf Notes</p>	
<p>2. Products consigned to (Consignee's name, address, country)</p> <p>VIET ASIAN WINDOW ASEANWINDOW CO., LTD ADD: A7/40 HAMLET 1 VINH LOC B WARD, BINH CHANH DISTRICT, HO CHI MINH CITY, VIET NAM TEL: 0084-982960935</p>		<p>4. For Official Use</p> <p><input type="checkbox"/> Preferential Treatment Given</p> <p><input type="checkbox"/> Preferential Treatment Not Given (Please state reason/s)</p> <p>Verification: origin.customs.gov.cn</p> <p>Signature of Authorised Signatory of the Importing Party</p>	
<p>3. Means of transport and route (as far as known)</p> <p>Departure date NOV. 15, 2023</p> <p>Vessel's name / Aircraft etc. FENGYUNHE / V. 1854S</p> <p>Port of Discharge HAIPHONG, VIET NAM</p> <p>FROM NANSHA, CHINA TO HAIPHONG, VIET NAM BY SEA</p>		<p>5. Item Number</p> <p>6. Marks and numbers on packages</p> <p>7. Number and type of packages, description of products (including quantity where appropriate and HS number in six digit code)</p> <p>8. Origin criteria (see Overleaf Notes)</p> <p>9. Gross weight or net weight or other quantity, and value (FOB) only when RVC criterion is applied</p> <p>10. Number, date of invoices</p>	
1	NM	<p>NINE HUNDRED AND EIGHTY FOUR (984) BUNDLES OF XINGFA ALUMINIUM PROFILES SIZE : LENGTH (4-6)M (19-160)MM, HEIGHT (10-4-120)MM THICK (1.5-3)MM, WEIGHT (0.6-1-3.380)KG/METERS+2%</p> <p>HS CODE: 7604.21 *** **</p> <p>MANUFACTURER: GUANGDONG XINGFA ALUMINIUM CO., LTD NO. 5 INDUSTRIAL SECTION D, LEPING TOWN, SANSHUI CENTRAL SCIENCE AND TECHNOLOGY INDUSTRIAL ZONE, FOSHAN, GUANGDONG, CHINA</p>	<p>"PE"</p> <p>24960KGS G.W.</p> <p>FD2023A57-1 NOV. 15, 2023</p>
<p>11. Declaration by the exporter</p> <p>The undersigned hereby declares that the above details and statement are correct, that all the products were produced in _____ (Country)</p> <p>and that they comply with the origin requirements specified for these products in the Rules of Origin for the ACFTA for the products exported to _____ (Importing Country)</p> <p>Nanning, China, NOV. 18, 2023</p> <p>Place and date, signature of authorised signatory</p>		<p>12. Certification</p> <p>It is hereby certified, on the basis of control carried out, that the declaration by the exporter is correct.</p> <p>Nanning, China, NOV. 18, 2023</p> <p>Place and date, signature and stamp of certifying authority</p>	
<p>13.</p> <p><input type="checkbox"/> Issued Retroactively      <input type="checkbox"/> Exhibition</p> <p><input type="checkbox"/> Movement Certificate      <input type="checkbox"/> Third Party Invoicing</p>		<p>2372000145732</p>	

2210451924





**ALUMINIUM PROFILES QUALITY MILL CERTIFICATE OF XINGFA**

PRODUCT: WROUGHT ALUMINIUM ALLOY EXTRUDED PROFILES FOR POWDER COATING PROFILES No: E2023111102

CUSTOMER:	VIET ASIAN WINDOW ASEANWINDOW CO.,LTD		
ALLOY & TEMPER	6063 T5	DELIVERY DATE	2023-11-11
PROFILES	PB09	-WEIGHT (KG)	7.948
PACKING LIST NO.	FD2023A584		
PRODUCTION STANDARD : GB/T 5237.4-2017			

C/O VÀ C/O CHỈ CÓ HIỆU LỰC KHI ĐÍNH KÈM  
 PKX SỐ: ... 60x12.5x1.2x...  
 NGÀY: ... 19/11/2023 ...

Chemical Compose	ELEMENT	Mg	Si	Fe	Cu	Mn	Cr	Zn	Ti	Al	
	STANDARD (%)	0.45-0.90	0.20-0.60	≤ 0.35	≤ 0.10	≤ 0.10	≤ 0.10	≤ 0.10	≤ 0.10	≤ 0.10	Rem.
	TESTING RESULT(%)	0.514	0.413	0.134	0.013	0.013	0.005	0.007	0.028	0.028	Rem.

Tensile Test	TESTING ITEM	TENSILE STRENGTH Rm(N/mm <sup>2</sup> )	YIELD STRENGTH Rp0.2(N/mm <sup>2</sup> )	ELONGATION A <sub>50mm</sub> (%)	WEBSTER HARNDNESS (HW)
	STANDARD	≥160	≥110	≥8	≥8
	TESTING RESULT	188	162	9.5	10.0

**PROPERTIES OF ELECTROSTATIC POWDER COATING FILM**

TEST ITEM	STANDARD REQUEST	TEST RESULT	TEST ITEM	STANDARD REQUEST	TEST RESULT
THICKNESS (μm)	LOCAL THICKNESS ≥ 40	70	IMPACT RESISTANCE	NOT SHOW ANY SIGN OF CRACKING OR DETACHMENT	NO CRACKING DETACHMENT
GLOSS	3-30 ±5 31-70 ±7 71-100 ±10	PASS			
BOILING WATER RESISTANCE	NO DETACHMENT OR WRINKLE EXIST ON THE COATING SURFACE, BUT SOME DISPERSIVE MINUTE BLISTERS IS ACCEPTABLE, ADHENSION SHALL MEET GRADE 0	PASS	COLOR AND COLOR DIFFERENCE	BE BASICALLY CONSISTANT WITH COLOR SAMPLES. WHEN EVALUATE THE COLOUR BY INSTRUMENT TEST THE COLOUR DIFFERENCE ΔEab* BETWEEN THE SOLID COLOUR COATING BE NOT MORE THAN 1.5	PASS
DRY ADHESION	0 CLASS	0 CLASS	INDENTATION	THE INDENTATION ≥ 80	115
WET ADHESION	0 CLASS	0 CLASS	HYDROCHLORIC ACID RESISTANCE	COATING SURFACE NOT EXIST ANY BLISTER AND OTHER OBVIOUS CHANGES	PASS
BOILING WATER ADHESION	0 CLASS	0 CLASS	MORTAR RESISTANCE	THE COATING SURFACE SHALL NOT EXIST ANY DETACHMENT AND OTHER OBVIOUS CHANGES	PASS
SURFACE QUALITY		PASS	RESULT		
TOLERANCE (HIGHEST SERIES)		PASS			

779300-00  
 VĂN PHÒNG ĐẠI DIỆN TẠI HÀ NỘI CÔNG TY TNHH CỬA SỔ VIỆT CHÂU Á ANWINDOW S.MY - TP.



REMARK: 零百发

ISSUER: 办发

GUANGDONG XINGFA GROUP QUALITY CONTROL DEPARTMENT